


Steel ball
WA750



Grade	Benchmark	Roundness	Surface roughness	The same batch is different from each other
G40	JIS B1501	1um	Ra0.08	2um
	ISO3290			

How to order

WA750 - 1.588 -

TYPE Dr

Material chosen

 SUJ2(Hardness).....

 SUS440C(Hardness)....

 SUS304.....

 SUS316.....

D		Hardness	
Metric	Inch	SUJ2	SUS440
1	-	HV760~880	HV660~780
1.588	1/16"		
2	-		
2.381	3/32"		
2.5	-		
3	-	HRC60~55	HRC58~
3.175	1/8"		
3.969	5/32"		
4	-		
4.762	3/16"		
5	-		

D		Hardness	
Metric	Inch	SUJ2	SUS440
5.556	7/32"	HRC60~55	HRC58~
6	-		
6.35	1/4"		
7.144	9/32"		
7.938	5/16"		
9.525	3/8"		
11.112	7/16"		
12.7	1/2"		
15.878	5/8"		
19.05	3/4"		
22.225	7/8"		